

## *Physical Properties of Grizzly Grip*

Weight per Gallon:	12lbs.
Viscosity, Krebs Units:	67-72
Percent solids by Weight:	R
Application Temperature Range:	32°F - 95°F
Application Thickness, 2 Coats Dry:	25-28 mils
Flexibility:	Total Flexibility
Resilience:	Resilient in dry state
Abrasion Resistance	
Tabor Wheel, 1000 gr Load. 1000 Cycles:	30.5
Fire Resistance	
Flame Spread	ASTM E-162: 01
Smoke Generation:	ASTM E-662: 06
Salt Water Resistance:	100%
Freeze-Thaw Resistance:	-60°F to +254°F
Pot Life:	3 Hours
Shelf Life:	6 Months
Flash Time:	1-1/2 Hours to 3 Hours
Walk Time:	12 Hours
Time Between Coats:	1 to 3 Hours
Full Circle:	+ 4 Days